



PRODUCT: DrakaTechna Tropic 1.00mm (Drinking Water Quality)

Test	Specification	Test Method
DENSITY (g/cm ³)	1.25	DIN 53479
TENSILE STRENGTH AT BREAK (N/mm ²)	>- 15	DIN 16726 5.6
ELONGATION AT BREAK	> 250	Din 16726 5.6
TEAR STRENGTH (N/mm)	> 80	DIN 16726 5.8.2
DIMENSIONAL STABILITY	<- /2/	DIN 16726 5.13.1
COLD CRACK TEMP (°C)	-20 No crack	DIN 16726 5.14
RESISTANCE TO ARTIFICIAL WEATHERING (%)	<=20 change in tensile strength / elongation at break after 4500 MJ/m ²	DIN 16726 5.17
ROOT PENETRATION	No penetration	DIN 16726 5.14

The typical values refer to results obtained during quality control of various production batches. Evenproducts Limited assumes no responsibility for the use of this data.